



**VERDANT PCRPTF075 Series** is an RPET (Recycle Polyethylene Terephthalate) in flake form produced with either a Clear tint (**PCRPTF075Z**), Green tint (**PCRPTF075Z**) or Brown tint (**PCRPTF075X**).

Resin Property	Typical Value	Units	Test Method
Intrinsic Viscosity	0.70-0.80	dl/g	Supplier Method
Melt Index	30-40	g/10 min	Supplier Method
DSC Melting Point	248-252	°C	Supplier Method
Humidity	<1	%	Supplier Method
рН	7-8	-	Supplier Method
Density	0.25-0.4	g/cm <sup>3</sup>	Supplier Method
PVC	<=50	ppm	Supplier Method
Polyolefin	0	ppm	Supplier Method
Paper and Fiber	<=10	ppm	Supplier Method
Metal	0	ppm	Supplier Method
PET with Glue	0	ppm	Supplier Method
Size	8-10	mm	Supplier Method

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.