



Melt Flow: 7-15

Clear or Multiple Colors

VERDANT RRPC0715 Series is a reprocessed, recycle grade polycarbonate resin designed for compounders or color houses which has a melt flow range between 7-15 g/10 min. This product is available in mixed color (**VERDANT RRPC0715X**), black color (**VERDANT RRPC0715Y**), and clear/natural color (**VERDANT RRPC0715Z**).

Test	Value	Units	Test Method
Melt Flow Rate (300°C, 1.2kg)	7-15	g/10 min	ASTM D-1238
Filler Content	0.64%	%	TGA 2050
Moisture	0.02%	%	Loss on Drying
Melting Point	230	°C	ASTM D3418
Tensile Strength	8,086	psi	ASTM D638
Notched Izod Impact (73 °F)	≥ 8	ft-lb/in	ASTM D256

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.