



Melt Flow: 15-30

Clear or Multiple Colors

VERDANT RRPC1530 is a reprocessed, recycle grade polycarbonate resin designed for compounders or color houses which has a melt flow range between 15-30 g/10 min. This product is available in mixed color (**VERDANT RRPC1530X**) and clear/natural color (**VERDANT RRPC1530Z**).

Test	Test Method	Units	Value
Melt Flow Rate (300°C, 1.2kg)	ASTM D-1238	g/10 min	15-30
Filler Content	TGA 2050	%	0.64%
Moisture (Loss on Drying)	Supplier Method	%	0.02%
Melting Point	ASTM D3418	°C	230
Tensile Strength	ASTM D638	psi	8,086

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.