

## verdant RRPH0220X Recycled Homopolymer Polypropylene

Melt Flow: 2-20

**VERDANT RRPH0220X** is a post-industrial and post-consumer recycled, reprocessed, homopolymer polypropylene blend in mixed color designed for injection molding applications.

Resin Property	Typical Value	Units	Test Method
Melt Flow Rate, 230 °C/2.16 kg	2-20	g/10 min	ASTM D-1238
Ash Content	0-2.5	%	ASTM D-5630
Moisture	0.1-0.2	%	Supplier Method (Loss on Drying)
Tensile Strength	4,500-6,000	psi	ASTM D-638
Flexural Modulus	170,000-320,000	psi	ASTM D-790
Notched Izod Strength	0.3-1.5	ft-lbs/in	ASTM D-256

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

> Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060 Phone: 281-902-0900 Fax: 281-260-8096