



Melt Flow: 25-40

VERDANT RRPI2540Y is a post-industrial recycled, reprocessed, polypropylene copolymer resin available in black color intended for injection molding applications.

Resin Property	Typical Value	Units	Test Method
Melt Flow Rate, 230 °C/2.16 kg	25-40	g/10 min	ASTM D-1238
Ash	< 7	%	ASTM D-5630
Flexural Modulus	100,000-130,000 (690-900)	psi (MPa)	ASTM D-790
Notched Izod, 73°F (23°C)	≥ 3.0 (160)	ft-lb/in (J/m)	ASTM D-256

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.