

VINPOL™ AB3205

Acrylonitrile-Butadiene-Styrene

Melt Flow: 32.6

Specific Gravity: 1.04

VINPOL AB3205 is an acrylonitrile-butadiene-styrene resin with natural color.

Resin Property	Typical Value	Units	Test Method
Melt Flow, 220°C, 10 kg	32.6	g/10 min	ASTM D-1238
Specific gravity	1.04	-	ASTM D-792
Mold Shrinkage, MD (TD), 3.2mm	0.3-0.6 (0.3-0.6)	%	ASTM D-955
Tensile Strength at Yield, 5mm/min	5,800	psi	ASTM D-638
Flexural Strength, 2.8mm/min	8,900	psi	ASTM D-790
Flexural Modulus, 2.8mm/min	310,000	psi	ASTM D-790
HDT, 18.56 kgf/cm ² , 6.4mm, unannealed	181.4	°F	ASTM D-648
HDT, 4.6 kgf/cm ² , 6.4mm, unannealed	93	°C	ASTM D-648
Vicat Softening Temperature, B/50	206.6	°F	ISO 306
Flammability, @ 1.0, 1.5, 3.0 and 6.0mm	HB	-	UL 94
Notched Izod Impact Strength, 73° F (23°C), 1/8"	5.5	ft-lb/in	ASTM D-256
Rockwell Hardness	107	R-Scale	ASTM D-785

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060
Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 02/01/2024