







IndustrialLogic Series

MD0635UG

Medium Density Polyethylene

Melt Index: 6

Density: 0.935

VINPOL ENDURE MD0635UG is a 35 mesh, granular, high density polyethylene powder providing Extreme Stiffness, Impact Resistance, and Toughness. This product is specifically designed for rotomolding applications such as agricultural storage tanks, bulk containers and feeders where high abrasion resistance and an advanced UV12 package is required. This product is available in natural and custom pre-color versions.

The Vinpol Roto Evolution Series delivers next generation technology advances for rotational molders. Engineered and tested for high performance applications, this lineup offers expanded processing windows and differentiated UV resistant additive packages. The results are industry leading durability and impact with improved melt flow options.

| Resin Property | Typical Value | Units | Test Method |
|---|---------------|-------------------|-------------|
| Melt Index, 2.16 Kg at 190°C | 6 | g/10 min | ASTM D-1238 |
| Density | 0.935 | g/cm ³ | ASTM D-792 |
| Bulk Density | 34 +/- 5 | g/cm ³ | ARM |
| Flexural Modulus, Tangent | 100,000 (689) | psi (MPa) | ASTM D-790 |
| Tensile Yield Strength | 2,500 (17) | psi (MPa) | ASTM D-638 |
| UV12 Weathering Test | Pass | - | ASTM D-2565 |
| Heat Deflection Temperature, 66psi | 136 (58) | °F (°C) | ASTM D-648 |
| ARM Cold Temperature Impact, 1/8", - 40°F Conditioned, 10 lb Dart | 49 (66) | ft-lbs (J) | ARM |
| Flow Rate | < 30 | Seconds | ARM |

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.