



VINPOL™ EV0627

Ethylene Vinyl Acetate Copolymer

Melt Index: 5.7

% VA: 26.7%

VINPOL EV0627 is a 26.7% vinyl acetate copolymer (EVA) with excellent flexibility, low temperature toughness, and has high filler acceptance. This resin contains thermal stabilizer.

*Resin Property	Typical Value	Units	Test Method
Melt Index, 2.16 Kg at 190 °C	5.7	g/10 min	ASTM D-1238
Vinyl Acetate Content	26.7	wt%	Supplier Method
Density	0.953	g/cm ³	ASTM D-1505
Peak Melting Temperature	162 (72)	°F (°C)	Supplier Method
Vicat Softening Temperature	113 (45)	°F (°C)	Supplier Method
Tensile Strength at Break	>1,500 (>10)	psi (MPa)	Supplier Method
Elongation at Break, Type IV	>800	%	Supplier Method
1% Secant Flexural Modulus	3,300 (23)	psi (MPa)	Supplier Method
Durometer Hardness, 15 sec	82	Shore A	Supplier Method
Durometer Hardness, 15 sec	27	Shore D	Supplier Method

*This product is not intended for use in medical applications and should not be used in any such applications. All physical properties were measured on compression molded specimens.

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060
Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 4/2/2025