

NINPOL[™]EV4327

Ethylene Vinyl Acetate Copolymer

Melt Index: 43.0

% VA: 26.7%

VINPOL EV4327 is a 26.7% vinyl acetate copolymer (EVA) that has good compatibility with hydrocarbon and natural tackifiers and most waxes. It is suitable for making hot melt adhesives, sealants, and wax blends. This resin contains thermal stabilizer.

| *Resin Property | Typical Value | Units | Test Method |
|-------------------------------|---------------|-------------------|-----------------|
| Melt Index, 2.16 Kg at 190 °C | 43.0 | g/10 min | ASTM D-1238 |
| Vinyl Acetate Content | 26.7 | wt% | Supplier Method |
| Density | 0.946 | g/cm ³ | ASTM D-1505 |
| Peak Melting Temperature | 158 (70) | °F (°C) | Supplier Method |
| Vicat Softening Temperature | 133 (56) | °F (°C) | Supplier Method |
| Tensile Strength at Break | >580 (>4) | psi (MPa) | Supplier Method |
| Elongation at Break, Type IV | >800 | % | Supplier Method |
| 1% Secant Flexural Modulus | 3,100 (21) | psi (MPa) | Supplier Method |
| Durometer Hardness, 15 sec | 78 | Shore A | Supplier Method |
| Durometer Hardness, 15 sec | 22 | Shore D | Supplier Method |

*This product is not intended for use in medical applications and should not be used in any such applications. All physical properties were measured on compression molded specimens.

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.