



VINPOL™ GP088

Polyethylene Terephthalate

VINPOL GP088 is a PET copolymer with low acetaldehyde generation. It is designed for applications such as 5 gallon blow molded containers.

Resin Property	Typical Value	Units	Test Method
Intrinsic Viscosity	0.880 +/- 0.02	dl/g	Supplier Method
Moisture Content	0.30 max.	wt %	Supplier Method
Ash Content	0.02 max.	wt %	Supplier Method
Acetaldehyde	1.0 max.	ppm	Supplier Method
Color CIE LAB L* b*	91 +/- 2.0 -0.4 +/- 1.0		Supplier Method
Melting Point	245 +/- 3	°C	Supplier Method
Fine Particles	100 max.	ppm	Supplier Method
Bulk Density	0.89 +/- 0.05	g/cm ³	Supplier Method
Size	140 +/- 5.0	pcs/2g	Supplier Method

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.