



## VINPOL™ HD00763F

### High Density Polyethylene

Melt Index: 0.7

Density: 0.963

**VINPOL HD00763F** is a high density polyethylene homopolymer suitable for blown film applications where stiffness and barrier properties are important. This product meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

Resin Property	Typical Value	Units	Test Method
Melt Index, 2.16 Kg at 190°C	0.7	g/10 min	ASTM D-1238
Density	0.963	g/cm <sup>3</sup>	ASTM D-4883
Tensile Strength at Yield	4600	psi	ASTM D-638
Elongation at Break	350	%	ASTM D-638
Flexural Modulus, 1"x3"x0.125", tangent	250,000	psi	ASTM D-790A
ESCR, 100% Igepal, Cond. B	10	hrs	ASTM D-1693

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060  
Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 09/26/2018