



## VINPOL™ HD08H49

### High Density Polyethylene

HLMI: 8

Density: 0.949

**VINPOL HD08H49** is a natural, bi-modal HDPE copolymer designed with antioxidant/thermal stabilizers for extrusion applications such as utility pipe and blends with HDPE for conduit and corrugated pipe and sheet.

Resin Property	Typical Value	Units	Test Method
Melt Index, 2.16 Kg at 190°C 21.6 Kg at 190°C (HL)	0.05 8.0	g/10 min g/10 min	ASTM D-1238 ASTM D-1238
Density	0.949	g/cm <sup>3</sup>	ASTM D-4883
NCLS (Notched Constant Ligament Stress)	>1500	hrs	ASTM F-2136
ESCR, Condition A, 10% Igepal	>1500	hrs	ASTM D-1693
ESCR, Condition A, 100% Igepal	>1500	hrs	ASTM D-1693, Modified
ESCR, Condition B, 10% Igepal	>1500	hrs	ASTM D-1693
ESCR, Condition B, 100% Igepal	>1500	hrs	ASTM D-1693, Modified

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060  
Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 06/8/2020