

VINPOL™ LB01018C

Linear Low Density Polyethylene

Melt Flow: 1.0

Density: 0.918

VINPOL LB01018C is a butene linear low density polyethylene, designed for thin film applications requiring toughness and strength. Meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

Resin Property	Typical Value	Units	Test Method
Melt Flow	1.0	g/10 min	ASTM D-1238
Density	0.918	g/cc	ASTM D-792
Secant Modulus (MD/TD)	24,400/27,300	psi	ASTM D-882
Tensile Strength at Break (MD/TD)	6,300/4,500	psi	ASTM D-882
Tensile Break Elongation (MD/TD)	740/970	%	ASTM D-882
Dart Drop Impact	90	g	ASTM-1709
Elmendorf Tear Strength (MD/TD)	120/460	g	ASTM D-1922
Haze	13	%	ASTM-1003

Additive \ Suffix	-A	-B	-C	-D
<i>Antiblock</i>	High	-	Medium	High
<i>Slip</i>	-	-	Medium	High
<i>Antioxidant</i>	-	-	-	-
<i>Processing Aid</i>	-	-	Yes	-

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.