



## VINPOL™ LB03525 Series

### Linear Low Density Polyethylene

Melt Index: 3.5

Density: 0.925

**VINPOL LB03525** is a butene linear low density polyethylene suitable for cast film applications requiring high stiffness. Meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

Resin Property	Typical Value	Units	Test Method
Melt Index, 2.16 Kg at 190 °C	3.5	g/10 min	ASTM D-1238
Density	0.925	g/cm <sup>3</sup>	ASTM D-4883
Tensile Strength at Break (MD/TD)	4500/3000	psi	ASTM D-882
Elongation at Break (MD/TD)	700/800	%	ASTM D-882
Dart Drop Impact	90	g	ASTM D-1709A
Haze (cast)	2	%	ASTM D-1003

<i>Additive \ Suffix</i>	<i>-B</i>	<i>-C</i>
<i>Antiblock</i>	-	Medium
<i>Slip</i>	-	Medium

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060  
 Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 10/30/2018