

VINPOL™ PA630GFHY

30% Glass Filled, Heat Stabilized and Lubricated Polyamide 6

30% Glass Filled

Heat-Stabilized and
Lubricated

VINPOL PA630GFHY is a 30% glass fiber filled, heat-stabilized, and lubricated polyamide 6 resin designed for injection molded applications in black color.

Resin Property	Typical Value	Units	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D-792
Tensile Strength @ Yield	25,000 (170)	psi (MPa)	ASTM D-638
Tensile Elongation	3.0	%	ASTM D-638
Flexural Modulus	1,250,000 (8,600)	psi (MPa)	ASTM D-790
Flexural Strength	37,500 (260)	psi (MPa)	ASTM D-790
Notched Izod Impact, RT, 1/8" bar	2.0 (107)	ft-lb/in (J/m)	ASTM D-256
Deflection Temperature, 66 psi, 1/8" bar	500 (260)	°F (°C)	ASTM D-648
Deflection Temperature, 264 psi, 1/8" bar	480 (249)	°F (°C)	ASTM D-648

Note: Recommended drying conditions: 180 °F, 2 to 4 hours. Max moisture = 0.20%. Recommended processing conditions: melt temperature 500-560 °F, mold temperature 80-180°F, back pressure 50 psi

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.