

VINPOL™ PC020

Polycarbonate

Melt Flow: 2

Specific Gravity: 1.20

VINPOL PC020 is a polycarbonate resin offering high low-temperature impact strength combined with excellent mechanical properties, dimensional stability, good flow-ability, electrical properties and weather resistance. This grade is designed for compounding applications.

Resin Property	Typical Value	Units	Test Method
Melt Flow, 1.2kgf @ 300°C	2	g/10 min	ASTM D-1238
Specific Gravity	1.20		ASTM D-792
Mold Shrinkage, 3 mm	0.5-0.7	%	ASTM D-955
Water Absorption, 24 hrs @ 23°C	0.15	%	ASTM D-570
Tensile Strength, yld	10,400 (71.6)	psi (MPa)	ASTM D-638
Tensile Elongation, brk	150	%	ASTM D-638
Flexural Strength, yld	12,900 (89)	psi (MPa)	ASTM D-790
Flexural Modulus	324,000 (2,240)	psi (MPa)	ASTM D-790
Izod Impact, notched, 23°C, 1/8"	100 (980)	kgf-cm/cm (J/m)	ASTM D-256
HDT, 18.6 kgf/cm ²	135	°C	ASTM D-648
Coefficient of Linear Thermal Expansion	5~7E-05	mm/mm/°C	ASTM D-696
Volume Resistivity	4E16	Ohm-cm	ASTM D257
Dielectric Strength	30	kV/mm	ASTM D-149
ARC Resistance	120	Sec	ASTM D-495
Flammability, 1/16" thickness	V-2		UL 94

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.