

VINPOL™PC07U

Injection Molding Grade Polycarbonate

Melt Flow: 7.0

UV Stabilized

VINPOL PC070U Low flow polycarbonate resin with UV stabilizer (for outdoor and lighting applications) and UL HB flame rated. This product is designed for thicker molded sections without sinks.

| Resin Property | Typical Value | Units | Test Method |
|--|---------------|----------|-----------------|
| Melt Flow, 1.2kgf @ 300°C | 7.0 | g/10 min | ASTM D-1238 |
| Specific Gravity | 1.2 | - | ASTM D-792 |
| Mold Shrinkage, flow, 3.2mm | 0.5-0.7 | % | Supplier Method |
| Water Absorption, 23°C/equilibrium | 0.35 | % | ASTM D-570 |
| Water Absorption, 100°C/equlibrium | 0.58 | % | ASTM D-570 |
| Water Absorption, 24 hours | 0.15 | % | ASTM D-570 |
| Tensile Stress, yld, Type I, 50 mm/min | 62 | MPa | ASTM D-638 |
| Tensile Stress, brk, Type I, 50 mm/min | 65 | MPa | ASTM D-638 |
| Tensile Strain, yld, Type I, 50 mm/min | 7 | % | ASTM D-638 |
| Tensile Strain, brk, Type I, 50 mm/min | 110 | % | ASTM D-638 |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 93 | MPa | ASTM D-790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 2,340 | MPa | ASTM D-790 |
| Izod Impact, unnotched, 23°C | 3,204 | J/m | ASTM D-4812 |
| Izod Impact, notched, 23°C | 907 | J/m | ASTM D-256 |
| Vicat Softening Temp, Rate B/50 | 154 | °C | ASTM D-1525 |
| HDT, 0.45 MPa, 6.4 mm, unannealed | 137 | °C | ASTM D-648 |
| HDT, 1.82 MPa, 6.4 mm, unannealed | 132 | °C | ASTM D-648 |
| CTE, -40°C to 95°C, flow | 6.84E-05 | 1/°C | ASTM E-831 |
| UL Yellow Card, 94HB Flame Class Rating | 0.73 | mm | UL 94 |
| Light Transmission, 2.54mm | 88 | % | ASTM D-1003 |
| Haze, 2.54mm | 1 | % | ASTM D-1003 |
| Refractive Index | 1.586 | - | ASTM D-542 |
| Volume Resistivity | >1E+17 | Ohm-cm | ASTM D-257 |

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.