

## VINPOL™ PC175R2

### Injection Molding Grade Polycarbonate

Melt Flow: 17.5

Specific Gravity: 1.2

**VINPOL PC175R2** is a UL rated HB, non-halogenated medium flow injection molding grade polycarbonate designed for small and intricate parts. This product is UV stabilized and contains an internal mold release additive.

Resin Property	Typical Value	Units	Test Method
Melt Flow, 1.2kgf @ 300°C	17.5	g/10 min	ASTM D-1238
Specific Gravity	1.2		ASTM D-792
Mold Shrinkage, flow, 3.2mm	0.5-0.7	%	Supplier Method
Water Absorption, 23°C/sat	0.35	%	ISO 62
Moisture Absorption, 23°C/50% RH	0.15	%	ISO 62
Melt Volume Rate, MVR @ 300°C/1.2kg	21	cm <sup>3</sup> /10 min	ISO 1133
Light Transmission	88	%	ASTM D-1003
Haze	1	%	ASTM D-1003
Refractive Index	1.586	-	ASTM D-542
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D-638
Tensile Stress, brk, Type I, 50 mm/min	65	MPa	ASTM D-638
Tensile Strain, yld, Type I, 50 mm/min	7	%	ASTM D-638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D-638
Tensile Modulus, 5 mm/min	2,380	MPa	ASTM D-638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	93	MPa	ASTM D-790
Flexural Modulus, 1.3 mm/min, 50 mm span	2,340	MPa	ASTM D-790
Izod Impact, unnotched, 23°C	3,204	J/m	ASTM D-4812
Izod Impact, notched, 23°C	694	J/m	ASTM D-256
Vicat Softening Temp, Rate B/50	154	°C	ASTM D-1525
HDT, 1.82 MPa, 3.2 mm, unannealed	132	°C	ASTM D-648
CTE, -40°C to 95°C, flow	6.84E-05	1/°C	ASTM E-831
Volume Resistivity	>1E+17	Ohm-cm	ASTM D-257
Dielectric Strength, in air, 3.2mm	14.9	kV/mm	ASTM D-149
Relative Permittivity, 50/60 Hz	3.17	-	ASTM D-150
Relative Permittivity, 1 MHz	0.01	-	ASTM D-150
Hot Wire Ignition (PLC)	4	PLC Code	UL 746A
UL Yellow Card, 94HB Flame Class Rating	0.76	mm	UL 94
UV-light, water exposure/immersion	F1	-	UL 746C

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.