



VINPOL™ PH030NM

Homopolymer Polypropylene

Melt Flow: 3

Density: 0.9

VINPOL PH030NM is a clarified homopolymer polypropylene designed for extrusion and thermoforming applications. It exhibits high crystallinity and offers excellent mechanical properties, good transparency and is in compliance with FDA 21 CFR 177.1520.

Resin Property	Typical Value	Units	Test Method
Melt Flow, I2 @ 230°C	3	g/10 min	ASTM D-1238
Density	0.9	g/cm ³	ASTM D-792
Tensile Strength at Yield, 2 in/min (51 mm/min)	5,600 (39)	psi (MPa)	ASTM D-638
Elongation at Yield, 2 in/min (51 mm/min)	6	%	ASTM D-638
Flexural Modulus, 1% Secant, 0.051 in/min (1.3 mm/min)	280,000 (1,930)	psi (MPa)	ASTM D-790
Notched Izod Impact Strength, 73°F (23°C)	1.0 (50)	ft-lb/in (J/m)	ASTM D-256A
Heat Deflection Temperature, 4.6 kgf/cm ²	250 (121)	°F (°C)	ASTM D-648

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060
Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 09/26/2018