



VINPOL™ PH2515TFFY

15% Talc Filled Homopolymer Polypropylene Compound

Melt Flow: 25

15% Talc Filled

VINPOL PH2515TFFY is a 15% talc filled homopolymer polypropylene compound, available in black color.

Resin Property	Typical Value	Units	Test Method
Melt Flow Rate	25	g/10 min	ISO 1133
Density	1.01	g/cm ³	ISO 1183
Tensile Modulus	4,400 (30)	psi (MPa)	ISO 527
Tensile Strength	290,000 (2,000)	psi (MPa)	ISO 527
Notched Charpy Impact, 73°F (23°C)	1.2 (2.5)	ft-lb/in ² (kJ/m ²)	ISO 179

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060
Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 03/18/2025