



VINPOL™ PI081

Impact Copolymer Polypropylene

Melt Flow: 8

Density: 0.9

VINPOL PI081 is an impact copolymer polypropylene designed for injection molding applications. It has good cold temperature impact properties and blush resistance. Applications include automotive parts, battery cases and other industrial parts.

Resin Property*	Typical Value	Units	Test Method
Melt Flow (230°C/2.16 kg)	8	g/10 min	ASTM D-1238
Density	0.90	g/cm ³	ASTM D-792B
Tensile Strength at Yield, 2.0 in/min (51 mm/min)	3,700 (26)	psi (MPa)	ASTM D-638
Elongation at Yield, 2.0 in/min (50 mm/min)	8	%	ASTM D-638
Flexural Modulus, 1% Secant, 0.05 in/min (1.3 mm/min)	160,000 (1,105)	psi (MPa)	ASTM D-790A
Notched Izod Impact Strength, 73°F (23°C)	1.6 (85)	ft-lb/in (J/m)	ASTM D-256A
DTUL, 66 psi Unannealed	175 (79)	°F (°C)	ASTM D-648

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.

Vinmar Polymers America, LLC / 16825 Northchase Drive, Suite 1400, Houston, TX 77060
 Phone: 281-902-0900 Fax: 281-260-8096

Rev. Date 10/4/2019