



VINPOL™ PI1000

Impact Copolymer Polypropylene

Melt Flow: 100

Density: 0.91

VINPOL PI1000 is a high flow, reactor produced, impact copolymer polypropylene designed for injection molding applications and as a base resin for compounding. It has high rigidity and impact strength, as well as low shrinkage for an impact copolymer. Targeted applications include large electrical and electronics articles & TWIM containers, as well as a base resin for E&E and automotive compounds. This resin is compliant with FDA 21 CFR 177.1520 (C).

Resin Property	Typical Value	Units	Test Method
Melt Flow	100	g/10 min	ASTM D-1238
Density	0.91	g/cm ³	ASTM D-1505
Tensile Strength at Yield	4,550 (31)	psi (MPa)	ASTM D-638
Elongation at Break	<50	%	ASTM D-638
Flexural Modulus	256,000 (1,765)	psi (MPa)	ASTM D-790
Notched Izod Impact Strength, 23° C	0.73 (39)	ft-lb/in (J/m)	ASTM D-256
Notched Izod Impact Strength, 0° C	0.55 (29)	ft-lb/in (J/m)	ASTM D-256
Notched Izod Impact Strength, -20° C	0.46 (24)	ft-lb/in (J/m)	ASTM D-256
Heat Distortion Temperature	261 (127)	°F (°C)	ASTM D-648
Rockwell Hardness	95	R Scale	ASTM D-785

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.