



## VINPOL™ PI900S

### Impact Copolymer Polypropylene

Melt Flow: 90

Density: 0.90

**VINPOL PI900S** is an impact copolymer polypropylene with high ethylene-propylene rubber content. It contains anti-static and mold release additives. It has high melt flow with a good balance of strength and impact resistance. It is designed for general household goods, home appliances and thin-wall parts.

Resin Property	Typical Value	Units	Test Method
Melt Flow	90	g/10 min	ASTM D-1238
Density	0.90	g/cm <sup>3</sup>	ASTM D-792
Tensile Strength at Yield	3,700 (25)	kgf/cm <sup>2</sup> (MPa)	ASTM D-638
Tensile Strain at Break	<100	%	ASTM D-638
Flexural Modulus	220,000 (1,516)	psi (MPa)	ASTM D-790
Notched Izod Impact Strength, 23° C	0.7 (37)	ft-lb/in (J/m)	ASTM D-256
Notched Izod Impact Strength, -10° C	0.5 (27)	ft-lb/in (J/m)	ASTM D-256
Heat Deflection Temperature, 4.6kgf/cm <sup>2</sup>	257 (125)	°F (°C)	ASTM D-648

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.