



VINPOL™ PR290M

Random Copolymer Polypropylene

Melt Flow: 29

Density: 0.90

VINPOL PR290M is a random copolymer polypropylene designed for injection molding applications. It has a good combination of strength, transparency and dimensional stability. Targeted applications include food packaging containers, disposable syringes and home appliances. This product complies with FDA 21 CFR 177.1520 covering exposure to food.

Resin Property	Typical Value	Units	Test Method
Melt Flow Index	29	g/10 min	ASTM D-1238
Density	0.90	g/cm ³	ASTM D-792
Tensile Strength at Yield	4,270 (29)	psi (MPa)	ASTM D-638
Elongation at Break	>500	%	ASTM D-638
Flexural Modulus	171,000 (1,179)	psi (MPa)	ASTM D-790
Notched Izod Impact Strength, 73° F (23°C)	0.7 (39)	ft-lb/in (J/m)	ASTM D-256
Heat Deflection Temp., 4.6 kgf/cm ²	201 (94)	°F (°C)	ASTM D-648
Rockwell Hardness	85	R Scale	ASTM D-785

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.