



VINPOL™ PR800M

Random Copolymer Polypropylene

Melt Flow: 80

VINPOL PR800M is a high melt flow, controlled rheology, clarified random copolymer designed for short cycle, easy mold filling injection molding applications requiring high transparency and good impact resistance. Targeted applications include high transparency TWIM parts and general purpose large articles with good contact clarity. This product contains mold release.

Resin Property ¹	Typical Value	Units	Test Method
Melt Flow	80	g/10 min	ASTM D-1238B
Tensile Strength at Yield, 50mm/min	3,700 (25.5)	psi (MPa)	ASTM D-638
Tensile Elongation at Yield, 50mm/min	14	%	ASTM D-638
Flexural Modulus, 1% Secant, 1.3mm/min	140,000 (965)	psi (MPa)	ASTM D-790-1A
Notched Izod Impact Strength, 73°F (23° C)	1 (58)	ft-lb/in (J/m)	ASTM D-256A
Gardner Impact, 73°F (23° C)	320 (36)	in-lb (J)	ASTM D-5420A

¹Type 1 specimen, 3.2mm thick injected according to ASTM D-4101 09 method.

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.