

## VINPOL™ PS0302-2

### High Impact Polystyrene

Melt Flow: 3

Natural, Water Clear

**VINPOL PS0302-2** is a natural, water clear HIPS designed for sheet extrusion applications, such as point of purchase displays and deep draw thermoforming. It also is suitable for blends with GPPS for disposable packaging, cups and plates. This product meets all requirements of the U. S. Food and Drug Administration as specified in 21 CFR 177.1640.

Resin Property	Typical Value	Units	Test Method
Melt Flow Rate, (200 °C/5.0kg)	3	g/10 min	ASTM D-1238
Specific Gravity	1.04	g/cm <sup>3</sup>	ISO-1183
Tensile Modulus	290,000 (2,000)	psi (MPa)	ASTM D-638
Tensile Strength at Break	2,800 (30)	psi (MPa)	ASTM D-638
Break Elongation	50	%	ASTM D-638
Notched Izod Impact (0.50 in)	2.2 (117)	ft-lb/in (J/m)	ASTM D-256
Vicat Temperature	194 (90)	°F (°C)	ASTM D-1525
HDT @ 264 PSI (Unannealed)	176 (80)	°F (°C)	ASTM D648
Flammability	HB	-	UL 94

Vinmar Polymers America cannot anticipate or control the many different conditions under which this information and/or product may be used. It does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. User of the material should make their own tests to determine the suitability of each such product for their particular purposes. The data listed herein falls within the normal range of product properties, but they should not be used to establish specification limits or used alone as the basis of design.